

CHEMICAL COMPOSITION (IN PERCENTAGE)

Grade	C (Max)	Mn (Max)	P (Max)	S (Max)	Si (Max)	Cr	Ni	Mo	Nitrogen (Max)	Cu/ Others
201	0.15	5.50/7.50	0.06	0.030	1.0	16.0/18.0	3.5/5.5	-	-	n-25 max
202	0.15	7.50/10.0	0.06	0.030	1.0	17.0/19.0	4.0/6.0	-	-	n-25 max
JS- 203	0.08	9.25/10.25	0.070	0.030	0.75	14.25 - 15.25	2.25 - 2.75	-	-	1.60- 2.0
301	0.15	2.00	0.045	0.030	1.00	16.00 - 18.00	6.00 - 8.00	-	0.10	-
301M	0.10	4.5/5.5	0.060	0.030	0.75	14.50 - 15.50	6.0 - 7.0	-	-	1.70- 1.90
304	0.08	2.00	0.045	0.030	0.75	18.00 - 20.00	8.00- 10.50	-	0.10	-
304L	0.030	2.00	0.045	0.030	0.75	18.00 - 20.00	8.00- 12.00	-	0.10	-
309s	0.08	2.0	0.045	0.030	1.0	22.0/24.0	12.0/15.0			
310	0.25	2.0	0.045	0.030	1.50	24.0/26.0	19.0/22.0			
310S	0.08	2.00	0.045	0.030	1.50	24.00- 26.00	19.00 - 22.00	-	-	-
316	0.08	2.00	0.045	0.030	0.75	16.00 - 18.00	10.00 - 14.00	2.00 - 3.00	0.10	-
316L	0.030	2.00	0.045	0.030	0.75	16.00 - 18.00	10.00 - 14.00	2.00 - 3.00	0.10	-
317	0.08	2.00	0.045	0.030	0.75	18.00 - 20.00	11.00 - 14.00	3.00 - 4.00	0.10	-
317L	0.030	2.00	0.045	0.030	0.75	18.00 - 20.00	11.00 - 15.00	3.00 - 4.00	0.10	-
321	0.08	2.00	0.045	0.030	0.75	17.00 - 19.00	9.00 - 12.00	-	0.10	Ti5 (C + N) Min or 0.70 max
347	0.08	2.00	0.045	0.030	0.75	17.00 - 19.00	9.00 - 13.00	-	-	Cb= 10x (C Min) or 1.00 Max
409	0.08	1.00	0.040	0.010	1.00	10.50 - 11.75	0.50	-	-	Ti= 6x (C+ N) Min or 0.70 Max
409M	0.03	0.8/1.2	0.030	0.030	0.40/0.75	11.00- 12.00	1.5 max.	-	-	Ti= 6x (C) Min or 0.70 Max
410S	0.08	1.00	0.040	0.030	1.00	11.50- 13.50	0.60	-	-	-
410	0.15	1.00	0.040	0.030	1.00	11.50- 13.50	0.75	-	-	-
420	0.35	0.50	0.035	0.015	0.50	12.00 - 13.00	0.20/3	-	-	-
440A	0.60/0.70	1.0	0.040	0.030	1.0	16.0/18.0	-	-	-	-
440B	0.75,0.95	1.0	0.040	0.030	1.0	16.0/18.0	-	-	-	-
440C	0.95, 1.2	1.0	0.040	0.030	1.0	16.0/18.0	-	-	-	-

430	0.12	1.00	0.040	0.030	1.00	16.00 - 18.00	0.75	-	-	-
JSL AUS	0.08	7.08.0	0.070	0.030	0.75	15.50 - 16.50	4.25 - 4.75	-	-	0.9 - 1.10
904L	0.02	2.00	0.030	0.045	1.00	19.0-23.0	23.0-28.0	-	-	23.0-28.0
2205	0.03	2.00	0.030	0.020	1.00	21.0-23.0	4.5-6.5			4.5-6.5
2207	0.030	1.20	0.035	0.020	0.30	24.0-26.0	6.0-8.0	-	-	6.0-8.0
* Thickness of 1.27mm & below will have elongation of 20% min.										